



Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China.Tel:86-769-3893 3228Email:utl@gdutl.comhttp://www.gdutl.com

TEST REPORT UN38.3, Seventh Edition Recommendations on transport of dangerous goods, manual of test and criteria,

Page 2 of 19

Section 38.3 -	Lithium metal and lithium ion Batteries
0	
Date of issue	2022-03-07
Fotal number of pages	19 pages
Testing Laboratory	GUANGDONG UTL CO., LTD.
Address	Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China.
Applicant's name:	Ultramax Batteries Limited
Address:	Watkins House,Pegamoid Rd.,London N18 2NG
Factory's name:	Ultramax Batteries Limited
Address:	Watkins House,Pegamoid Rd.,London N18 2NG
Phone number:	+44-02088038899
Email:	
Website:	N/A
Test specification	
Standard	ST/SG/AC.10/11/Rev.7/Section 38.3
Fest procedure:	N/A
Non-standard test method	N/A
Test item description	LITHIUM BATTERY
Trade Mark:	N/A
Model/Type reference:	24V 50Ah
Ratings:	25.6V, 50Ah, 1280Wh

Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China. Tel: 86-769-3893 3228 Email: utl@gdutl.com http: //www.gdutl.com

Page 3 of 19 Summary of testing: Tests performed (name of test and test clause): Test Conclusion Test(s) Conclusion T.1: Altitude simulation Pass T.2: Thermal test Pass T.3: Vibration Pass Pass T.4: Shock T.5: External short circuit Pass T.6: Impact Pass T.7: Overcharge Pass T.8: Forced discharge Pass Sample Status: Test(s) Sample Number Sample Status at first cycle, in fully charged states. SLine-2-1 - SLine-2-4 T.1~T.5 after twenty-fifth cycles ending in fully charged states. SLine-2-5 - SLine-2-8 at first cycle at 50% of the design rated capacity. SineL-1-1 - SineL-1-5 after twenty-fifth cycles ending at 50% of the design rated T.6 capacity. SineL-1-6 - SineL-1-10 at first cycle, in fully charged states. SLine-2-9 - SLine-2-12 T.7 after twenty-fifth cycles ending in fully charged states. SLine-2-13 - SLine-2-16 at first cycle, in fully discharged states. SLine-1-11 - SLine-1-20 T.8 after twenty-fifth cycles ending in fully discharged states. SLine-1-21 - SLine-1-30 The test results: Pass


TEST REPORT

Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China. Tel: 86-769-3893 3228 Email: utl@gdutl.com http://www.gdutl.com

A. A.	FEST F	REPO	RT		
	and the second s			and the second s	Page 4 of 19
Test item particulars					
Cell type Nominal Voltage of cell		32700 3.2V	UTIP .	Ś	
Rated Capacity of cell					
Battery Type		: Lithium ion b	attery	THE	ć
Appearance	:	Black			
Number of cell Dimension(mm)	Ś	: 72pcs (8S9P : 329.0mm(ma) ax) × 172.0mm((max) ×214.0	mm(max)
Test case verdicts					
Test case does not apply to the test	object	: N/A		THE	ć
Test item does meet the requirement	nt	: P(Pass)			
Test item does not meet the require	ment	F(Fail)	ALL		
Testing				C	
Date of receipt of test item		2022-02-15			
Date(s) of performance of test		: 2022-02-15 t	o 2022-03-04	AT A	
General remarks	\sim			0	0
This report shall not be reproduced	l, except in full, wi	thout the writte	n approval of t	he testing lab	oratory.
The test results presented in this re	port relate only to	o the item tested	d.		~
"(see remark #)" refers to a remark	appended to the	report.	(1)		<u>I</u>
Throughout this report a point is us	ed as the decima	l separator.			
According to the Standard, a single be tested according to the testing r and Battery Cell as aforementioned individual test record.	equirements for "	Cell". This testir	ng included the	e samples of	Battery Pack

 Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China.

 Tel:
 86-769-3893 3228
 Email: utl@gdutl.com
 http: //www.gdutl.com





Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China.Tel:86-769-3893 3228Email: utl@gdutl.comhttp://www.gdutl.comhttp://www.gdutl.com

Page 6 of 19

Clause 38.3.4.1 38.3.4.2	Requirement + Test	Result - Remark	Verdict
	1		
38.3.4.1	Test T.1: Altitude simulation		Р
- Alle	Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature (20±5°C)	QUIC QUI	Р
S OTTO	Cells and batteries meet this requirement if there i no leakage, no venting, no disassembly, no ruptur and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.	e disassembly, no rupture and no fire.	P
38.3.4.2	Test T.2: Thermal test		P
THE	Test cells and batteries are to be stored for at least six hours at a test temperature equal to $72\pm2^{\circ}$ C, followed by storage for at least six hours at a test temperature equal to - $40\pm2^{\circ}$ C. The maximum tim- interval between test temperature extremes is 30 minutes. This procedure is to be repeated 10 times, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20 $\pm 5^{\circ}$ C).		Р
3			
	For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.		Р
(fill)	Cells and batteries meet this requirement if there i no leakage, no venting, no disassembly, no ruptur and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.	e disassembly, no rupture and no fire.	P

 Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China.

 Tel:
 86-769-3893-3228

 Email:
 utl@gdutl.com

 http://www.gdutl.com

Page 7 of 19

Clause	Requirement + Test	Result - Remark		Verdict
38.3.4.3	Test T.3: Vibration			Р
, See	Cells and batteries are firmly secured to the platform of the vibration machine without distortin the cells in such a manner as to faithfully transmi the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times fo a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.	t z s	UNE UNE	P
- TH		Still.	STI	>
>	The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).		- The	P
-5-5-5-5-5-5-5-5-5-5-5-5-5-5-5-5-5-5-5	For cells and small batteries: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occur (approximately 50 Hz). A peak acceleration of 8 g is then maintained until the frequency is increase to 200 Hz.	s gn	UTIE -	P
J'II	For large batteries: from 7 Hz to a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 gn occurs (approximately 25 Hz). A peak acceleration of 2 g is then maintained until the frequency is increase to 200 Hz.	s gn	-JUE	N/A
8				

 Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China.

 Tel:
 86-769-3893 3228
 Email: utl@gdutl.com

Page 8 of 19

Clause	Requirement + Test	Result - Remark	Verdict
- Call	Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery directly after testing in its third perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.	No leakage, no venting, no disassembly, no rupture and no fire. See test data for details.	P
38.3.4.4	Test T.4: Shock	A 4	P
00	Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.	920 92	P
e la	Shock: a half-sine shock of peak acceleration of 150 gn (or Acceleration(gn)= $\sqrt{\frac{100850}{mass}}$, which is smaller) and pulse duration of 6 milliseconds, large cells and large batteries shall be subjected to a half-sine or peak acceleration of 50 gn (or Acceleration(gn)= $\sqrt{\frac{30000}{mass}}$, which is smaller) and pulse duration of 11 milliseconds/对小电芯或小电	50 550 550	Ρ
5	Ster Ster	60 - 560	
-S ^B	Each cell or battery shall be subjected to three shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.	550 55	Р
		10 A A A A A A A A A A A A A A A A A A A	

Address: Lianding Testing Building, No,18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China. Tel: 86-769 3893 3228 Email: utl@gdbtt.com http://www.gdutl.com

Page 9 of 19

Clause	UN 38.3		
Clause	Requirement + Test	Result - Remark	Verdict
of the	Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.	No leakage, no venting, no disassembly, no rupture and no fire. See test data for details.	P
38.3.4.5	Test T.5: External short circuit		Р
- THE	The cell or battery to be tested shall be temperature stabilized so that its external case temperature reaches 57±4°C.	and and	P
>	The cell or battery at 57 \pm 4°C shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57 \pm 4°C, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value.		P
2	Cells and batteries meet this requirement if their external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.	No disassembly, no rupture and no fire. See test data for details.	P
38.3.4.6	Test T.6: Impact / Crush		P
	Test procedure – Impact (applicable to cylindrical cells not less than 18.0 mm in diameter)	Cylindrical cell more than 18.0 mm in diameter	Р

 Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China.

 Tel:
 86-769-3893 3228
 Email: utl@gdutl.com
 http: //www.gdutl.com

Page 10 of 19

/	UN 38.3	V V	
Clause	Requirement + Test	Result - Remark	Verdict
	The sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm±0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg±0.1 kg mass is to b dropped from a height of 61±2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling		P
- TH	mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.	STAR.	STE
>	The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm±0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.		P
- Sta	Test Procedure – Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18.0 mm in diameter).	Cylindrical cell more than mm in diameter	18.0 N/A
2	A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual wit a speed of approximately 1.5 cm/s at the first poin of contact. The crushing is to be continued until the first of the three options below is reached. /	ty 🔍	N/A
	(a) The applied force reaches 13 kN±0.78 kN;	\sim	N/A
	(b) The voltage of the cell drops by at least 100 mV;		N/A
6	(c) The cell is deformed by 50% or more of its original thickness.		N/A

Page 11 of 19

·	UN 38.3		
Clause	Requirement + Test	Result - Remark	Verdict
ST.	A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.	STE ST	Р
5			
, A	Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.		P
- Sur			
	Cells and component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassembly and no fire during the test and within six hours after this test.	No disassembly and no fire. / See test data for details. /	P
5	atte atte		<
38.3.4.7	Test T.7: Overcharge		Р
TH	The charge current shall be twice the manufacturer's recommended maximum continuous charge current. Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours. The minimum voltage of the test shall be as follows:		P
3	(a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.		N/A
Qn	(b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.	The voltage of the test is 35.04V, and the current is 100A.	P
3	There is no disassembly and no fire during the test	No disassembly and no	P
7	and within seven days after the test.	fire. /	

Page 12 of 19

Clause	Requirement + Test	Result - Remark	Verdict
38.3.4.8	Test T.8: Forced discharge		Р
- Sec	Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.	alle 4	P
	The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).		<
State	STAR STAR	attle a	5 ¹⁰
	There is no disassembly and no fire during the test and within seven days after the test.	No disassembly and no fire See test data for details.	. P



Test Data

Page 13 of 19

T.1 (Altitude simulation)

			/	∕∽		1	~
Sample	Before test		After	After test		Change ratio	Results
No.	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)	(%)	(%)	
SLine-2-1	11422	26.91	11422	26.91	0.000	100.000	Р
SLine-2-2	11422	26.91	11422	26.90	0.000	99.963	Р
SLine-2-3	11421	26.90	11421	26.90	0.000	100.000	Р
SLine-2-4	11422	26.91	11422	26.91	0.000	100.000	Р
SLine-2-5	11421	26.91	11421	26.91	0.000	100.000	Р
SLine-2-6	11422	26.91	11422	26.90	0.000	99.963	Р
SLine-2-7	11422	26.91	11422	26.90	0.000	99.963	Р
SLine-2-8	11422	26.91	11422	26.91	0.000	100.000	Р
Note:	0×		\odot	\odot	~	(O)	C

Note:

A. Leakage B. Venting; C. Disassembly; D. Rupture; E. Fire P. No leakage, no venting, no disassembly, no rupture, no fire

T.2 (Thermal test)

	())`	$()^{\vee}$		
Before test		After test		Mass loss	Change ratio	Results
Mass (g)	Voltage (V)	Mass (g)	Voltage (V)	(%)	(%)	
11422	26.91	11421	26.01	0.009	96.656	Р 🏑
11422	26.90	11422	26.00	0.000	96.654	Р
11421	26.90	11421	25.92	0.000	96.357	Р
11422	26.91	11422	26.01	0.000	96.656	S P
11421	26.91	11421	26.04	0.000	96.767	Р
11422	26.90	11422	25.95	0.000	96.468	Р
11422	26.90	11422	26.05	0.000	96.840	Р
11422	26.91	11422	25.97	0.000	96.507	Р
	Mass (g) 11422 11422 11421 11422 11421 11422 11422 11422	Mass (g)Voltage (V)1142226.911142226.901142126.901142226.911142126.911142226.901142226.901142426.90	Mass (g) Voltage (V) Mass (g) 11422 26.91 11421 11422 26.90 11422 11421 26.90 11422 11421 26.90 11421 11422 26.91 11421 11421 26.90 11422 11422 26.91 11422 11421 26.91 11421 11422 26.91 11422 11422 26.90 11422 11422 26.90 11422	Mass (g) Voltage (V) Mass (g) Voltage (V) 11422 26.91 11421 26.01 11422 26.90 11422 26.00 11421 26.90 11421 25.92 11422 26.91 11422 26.01 11422 26.91 11422 26.01 11421 26.91 11422 26.01 11422 26.91 11422 26.04 11422 26.90 11422 25.95 11422 26.90 11422 25.95 11422 26.90 11422 26.05	Mass (g) Voltage (V) Mass (g) Voltage (V) Mass loss (%) 11422 26.91 11421 26.01 0.009 11422 26.90 11422 26.00 0.000 11421 26.90 11421 25.92 0.000 11422 26.91 11422 26.01 0.000 11422 26.91 11422 26.01 0.000 11421 26.91 11421 26.04 0.000 11421 26.91 11422 26.04 0.000 11422 26.90 11422 25.95 0.000 11422 26.90 11422 26.05 0.000	Mass (g) Voltage (V) Mass (g) Voltage (V) Mass loss (%) Change ratio (%) 11422 26.91 11421 26.01 0.009 96.656 11422 26.90 11422 26.00 0.000 96.654 11421 26.90 11421 25.92 0.000 96.656 11422 26.91 11422 26.01 0.000 96.656 11422 26.91 11422 26.01 0.000 96.656 11422 26.91 11422 26.01 0.000 96.656 11422 26.91 11422 26.04 0.000 96.656 11421 26.91 11421 26.04 0.000 96.767 11422 26.90 11422 25.95 0.000 96.468 11422 26.90 11422 26.05 0.000 96.840

Note:

A. Leakage; B. Venting; C. Disassembly; D. Rupture; E. Fire P. No leakage, no venting, no disassembly, no rupture, no fire/

Page 14 of 19

Test Data

T.3 (Vibration)

		~			\sim			~	
	Sample No.	Before test		After	After test		Change ratio	Results	
		Mass (g)	Voltage (V)	Mass (g)	Voltage (V)	(%)	(%)		
	SLine-2-1	11421	26.01	11421	26.01	0.000	100.000	Р	
C	SLine-2-2	11422	26.00	11422	26.00	0.000	100.000	Р	
	SLine-2-3	11421	25.92	11421	25.92	0.000	100.000	Р	
	SLine-2-4	11422	26.01	11422	26.01	0.000	100.000	Р	
	SLine-2-5	> 11421	26.04	11421	26.04	0.000	100.000	р Р	
	SLine-2-6	11422	25.95	11422	25.95	0.000	100.000	Р	
	SLine-2-7	11422	26.05	11422	26.03	0.000	99.923	Р	
	SLine-2-8	11422	> 25.97	11422	25.97	0.000	100.000	Р	\otimes
6	Note [.]	O.			\odot	17	U.	C	

Note:

A. Leakage; B. Venting; C. Disassembly/; D. Rupture; E. Fire

P. No leakage, no venting, no disassembly, no rupture, no fire


T.4 (Shock)

	\sim		\sim	\bigcirc		7	
Before test		After test		Mass loss	Change ratio	Results	
Mass (g)	Voltage (V)	Mass (g)	Voltage (V)	(%)	(%)		
11421	26.01	11421	26.00	0.000	99.962	Р	
11422	26.00	11422	26.00	0.000	100.000	Р	
11421	25.92	11421	25.92	0.000	100.000	Р	
11422	26.01	11422	26.01	0.000	100.000	S P	
11421	26.04	11421	26.04	0.000	100.000	Р	
11422	25.95	11422	25.94	0.000	99.961	Р	
11422	26.03	11422	26.03	0.000	100.000	Р	
11422	> 25.97	11422	25.97	0.000	100.000	Р	
	Mass (g) 11421 11422 11421 11422 11421 11422 11422 11422	Mass (g) Voltage (V) 11421 26.01 11422 26.00 11421 25.92 11422 26.01 11421 25.92 11422 26.01 11421 25.92 11422 26.01 11421 26.04 11422 25.95 11422 26.03	Mass (g) Voltage (V) Mass (g) 11421 26.01 11421 11422 26.00 11422 11421 25.92 11421 11422 26.01 11422 11421 25.92 11421 11422 26.01 11422 11421 26.04 11421 11422 25.95 11422 11422 26.03 11422	Mass (g)Voltage (V)Mass (g)Voltage (V)1142126.011142126.001142226.001142226.001142125.921142125.921142226.011142226.011142126.041142126.041142225.951142225.941142226.031142226.03	Mass (g) Voltage (V) Mass (g) Voltage (V) Mass loss (%) 11421 26.01 11421 26.00 0.000 11422 26.00 11422 26.00 0.000 11421 25.92 11421 25.92 0.000 11422 26.01 11422 26.01 0.000 11422 26.01 11422 26.01 0.000 11421 26.04 11421 26.04 0.000 11422 25.95 11422 25.94 0.000 11422 26.03 11422 26.03 0.000	Mass (g) Voltage (V) Mass (g) Voltage (V) Mass loss (%) Change ratio (%) 11421 26.01 11421 26.00 0.000 99.962 11422 26.00 11422 26.00 0.000 100.000 11421 25.92 11421 25.92 0.000 100.000 11422 26.01 11422 26.01 0.000 100.000 11422 26.01 11422 26.01 0.000 100.000 11421 25.92 11421 26.04 0.000 100.000 11422 26.03 11422 26.04 0.000 100.000 11422 25.95 11422 25.94 0.000 99.961 11422 26.03 11422 26.03 0.000 100.000	

Note:

A. Leakage; B. Venting; C. Disassembly; D. Rupture; E. Fire P. No leakage, no venting, no disassembly, no rupture, no fire





T.5 (External short circuit)


Sample No.	Total circuit Resistance (mΩ)	Maximum Temperature, C	Results
SLine-2-1	71.3	58.0	Р
SLine-2-2	73.0	58.0	Р
SLine-2-3	80.1	57.6	Р
SLine-2-4	75.9	57.4	Р
SLine-2-5	79.8	58.0	Р
SLine-2-6	77.0	57.7	Р
SLine-2-7	74.0	57.7	P
SLine-2-8	73.9	57.5	Р

T.6 (Impact)

Sample No.	Voltage before Test (V)	Maximum Temperature, C	Results
SineL-1-1	3.282	22.4	Р
SineL-1-2	3.284	22.3	Р
SineL-1-3	3.283	23.6	P
SineL-1-4	3.289	22.6	Р
SineL-1-5	3.281	22.9	Р
SineL-1-6	3.283	22.8	Р
SineL-1-7	3.287	23.7	P
SineL-1-8	3.290	22.5	P
SineL-1-9	3.284	22.3	Р
SineL-1-10	3.283	22.5	Р
Note: A. Disassembly; B. P. No disassembly,	Fire no fire within 6 hours after the t	est	







T.7 (Overcharge)

Sample No.	Voltage before (V)	Test	Results
SLine-2-9	26.91		Р
SLine-2-10	26.90		Р
SLine-2-11	26.91	ALC: NO	Р
SLine-2-12	26.84	0	Р
SLine-2-13	26.88		Р
SLine-2-14	26.90		Р
SLine-2-15	26.86		P
SLine-2-16	26.85		Р

T.8 (Forced discharge)

	Sample No.	Voltage before Test (V)	Sample No.	Voltage before Test (V)	Results
	SLine-1-11	2.665	SLine-1-21	2.668	Р
	SLine-1-12	2.661	SLine-1-22	2.664	Р
	SLine-1-13	2.658	SLine-1-23	2.659	P A
C	SLine-1-14	2.659	SLine-1-24	2.656	Р
	SLine-1-15	2.660	SLine-1-25	2.655	Р
	SLine-1-16	2.662	SLine-1-26	2.650	Р
	SLine-1-17	2.656	SLine-1-27	2.667	P
	SLine-1-18	2.656	SLine-1-28	2.652	Р
	SLine-1-19	2.655	SLine-1-29	2.657	Р
	SLine-1-20	2.662	SLine-1-30	2.657	Р
Ś	Note/ A. Disassembly; B. 1 P. No disassembly, n	Fire o fire within seven day	s after the test/	fill (



Figure 1 Overall view I of battery




Figure 2 Overall view II of battery

S.

Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China. Tel: 86-769-3893 3228 Email: utl@gdutl.com http: //www.gdutl.com



Page 18 of 19

Photos




Figure 3 Overall view of cell



Figure 4 Battery Label

Address: Lianding Testing Building, No.18 Center Road of Yayuan Industrial Zone, Nancheng District, Dongguan, Guangdong, China. Tel: 86-769-3893 3228 Email: utl@gdutl.com http: //www.gdutl.com

